

## OK Tigrod 316LSi

Bare corrosion resisting chromium-nickel-molybdenum rods for welding of austenitic stainless alloys of 18% Cr-8% Ni and 18% Cr-10% Ni-3% Mo types. OK Tigrod 316LSi has a good general corrosion resistance, in particularly the alloy has very good resistance against corrosion in acid and chlorinated environments. The alloy has a low carbon content which makes it particularly recommended where there is a risk of intergranular corrosion. The higher silicon content improves the welding properties, such as wetting. The alloy is widely used in the chemical and food processing industries as well as in ship building and various types of architectural structures.

Specifications	
<b>Classifications</b>	EN ISO 14343-A : W 19 12 3 L Si SFA/AWS A5.9 : ER316LSi Werkstoffnummer : ~1.4430
<b>Approvals</b>	BV : 316L BT CE : EN 13479 DB : 43.039.06 DNV-GL : VL 316 L (I1) UKCA : EN 13479 VdTÜV : 05336

Approvals are based on factory location. Please contact ESAB for more information.

<b>Alloy Type</b>	Austenitic (with approx. 8 % ferrite) 19% Cr - 12% Ni - 3% Mo - Low C- High Si
<b>Shielding Gas</b>	I1 (EN ISO 14175)

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
As Welded	500 MPa	630 MPa	33 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
As Welded	20 °C	175 J
As Welded	-110 °C	110 J
As Welded	-196 °C	90 J

Typical Weld Metal Analysis %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Shielding gas;Ar									
0.01	1.8	0.8	0.01	0.02	12	18	2.8	0.1	0.06

Typical Weld Metal Analysis %									
FN WRC-92									
Shielding gas;Ar									
7									

Typical Wire Composition %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.013	1.7	0.76	0.014	0.016	11.8	18.4	2.6	0.1	0.055

Typical Wire Composition %									
FN WRC-92									
7									